

Material - ASTM A 479 310Cb

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 479 310Cb Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 max.	Solution Annealing	
Silicon	Si %	1.500 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	24.000 - 26.000		
Nickel	Ni %	19.000 - 22.000		
Niobium	Nb %	1.100 max.		-
Nitrogen	N %	0.100 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	515 min.
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
A240 UNS S31040	ASTM	USA	Steel, Plate, Sheet and Strip	
310 Cb	SAE	USA	Steel	
A213 TP 310Cb	ASTM	USA	Steel and Tube	
A249 TP 310Cb	ASTM	USA	Steel and Tube	
A276 310Cb	ASTM	USA	Steel, Bar and Shapes	
A358 310Cb	ASTM	USA	Steel and Pipe	
A959 Type 310Cb	ASTM	USA	Steel	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.