



Material - ASTM A 479 316Ti

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 479 316Ti Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	16.000 - 18.000		
Molybdenum	Mo %	2.000 - 3.000		
Nickel	Ni %	10.000 - 14.000	Mechanical Properties	
Titanium	Ti %	0.700 max.	Tensile Strength in Mpa	515 min.
Nitrogen	N %	0.100 max.	Yield Strength in Mpa	205 min.
Iron	Fe %	Balance	Elongation in %	30 min.
-	-	-	Reduction of Area in %	40 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S31635	ASTM	USA	Steel, Plate, Sheet and Strip
316Ti	AS	Australia	Steel, Sheet, Plate and Strip
316Ti	SAE	USA	Steel
STS 316 Ti	KS	Korea	Steel, Sheet, Plate and Strip
SUS 316 Ti	JIS	Japan	Steel, Wire and Rod
A276 316 Ti	ASTM	USA	Steel, Bar and Shapes
A314 316 Ti	ASTM	USA	Steel, Bar, Rolling and Forging

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.