

Material - ASTM A 479 439

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 479 439 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.070 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.	Annealing or Hardening + Tempering	
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	17.000 - 19.000		
Nickel	Ni %	0.500 max.		
Nitrogen	N %	0.040 max.		
Titanium	Ti %	1.100 max.	Mechanical Properties	
Aluminium	Al %	0.150 max.	Tensile Strength in Mpa	485 min.
Iron	Fe %	Balance	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	45 min.
-	-	-	Hardness in HB	192 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
A240 UNS S43035	ASTM	USA	Steel, Plate, Sheet and Strip	
S43035	UNS	USA	Steel	
A959 S43035	ASTM	USA	Steel	
439	SAE	USA	Steel	
A803 Grade TP 439	ASTM	USA	Steel and Tube	
A959 Type 439	ASTM	USA	Steel	
SA-240 439	ASME	USA	Steel	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.