



## Material - ASTM A 505 8630

Standard Specification for Alloy Steel, Sheet, Strip, Hot-Rolled and Cold-Rolled

**Group - Ferrous Mild Steel Alloys** 

Sub Group - ASTM A 505 8630 Alloy Steel, Sheet, Strip, Hot-Rolled and Cold-Rolled Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bar, Wire, Tube and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.280 - 0.330		
Silicon	Si %	0.150 - 0.300	As- Cast or Normalising or Annealing or Hardening + Tempering	
Manganese	Mn %	0.700 - 0.900		ancaling or Hardoning ±
Phosphorus	P %	0.040 max.		•
Sulphur	S %	0.040 max.		iiig
Chromium	Cr %	0.400 - 0.600		
Molybdenum	Mo %	0.150 - 0.250		
Nickel	Ni %	0.400 - 0.700		-
Iron	Fe %	Balance	Mechanical Properties	
-	-		Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A915 Grade SC 8630	UNS	USA	Casting		
J13095	UNS	USA	Bar, Wire, Tube and Forging		
A 29 8630	ASTM	USA	Bar, Wire, Tube and Forging		
8630	AISI	USA	Bar, Wire, Tube and Forging		
8630	SAE	USA	Bar, Wire, Tube and Forging		
8630	AMS	USA	Bar, Wire, Tube and Forging		
8630	AS	Australia	Bar, Wire, Tube and Forging		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.