



Material - ASTM A 510 1013

Standard Specification For General Requirements for Wire Rods

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 510 1013 General Requirements for Wire Rods

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Wire Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.110 - 0.160	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Boron	B %	0.0008 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	370 Min.
			Yield Strength in Mpa	310 min.
			Elongation in %	19 min.
			Reduction of Area in %	40 min.
			Hardness in HB	105 max.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10130	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1013	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1013	AISI	USA	Bar
A 1040 1013	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 29 1013	ASTM	USA	Bar
SA-29 1013	ASME	USA	Bar
K11430	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.