

Material - ASTM A 510 1017

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod and Round Wire

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 510 1017 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod and Round Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire Rod and Round Wire

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|---------------|--|-----------|
| Carbon | C % | 0.150 - 0.200 | | |
| Manganese | Mn % | 0.300 - 0.600 | As Raw or Annealing or Normalizing or Hardening and Tempering | |
| Phosphorus | P % | 0.040 Max. | | |
| Sulphur | S % | 0.050 max. | | |
| Boron | В% | 0.0008 max. | | |
| Iron | Fe % | Balance | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 370 - 410 |
| - | - | - | Yield Strength in Mpa | 200 min. |
| - | - | - | Elongation in % | 18 min. |
| - | - | - | Reduction of Area in % | 40 - 50 |
| - | - | - | Hardness in HB | 105 - 116 |
| - | - | - | Impact in Joule | - |

| Cross Reference Table | | | | | |
|-----------------------|----------|---------|------------------------------|--|--|
| Material | Standard | Country | Grade Belong to the Industry | | |
| G10170 | UNS | USA | Bars, Wire Rods and Tubing | | |
| 1017 | SAE | USA | Steel and Bar | | |
| 1017 | AISI | USA | Tubing | | |
| A 1040 1017 | ASTM | USA | Steel | | |
| A 29 1017 | ASTM | USA | Steel and Bar | | |
| A 29 M1017 | ASTM | USA | Steel and Bar | | |
| A 513 Grade 1017 | ASTM | USA | Tubing | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.