

Material - ASTM A 510 1023

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod and Round Wire

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 510 1023 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod and Round Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire Rod and Round Wire

Chemical Composition		Heat Treatment	
C %	0.200 - 0.250		
Mn %	0.300 - 0.600	As Raw or Annealing or Normalizing or Hardening and Tempering	
P %	0.040 max.		
S %	0.050 max.		
В%	0.0008 max.		
Fe %	Balance		
-	-		
-	-		
-	-	Mechanical Properties	
-	-	Tensile Strength in Mpa	370 - 430
-	-	Yield Strength in Mpa	210 min
-	-	Elongation in %	15 min.
-	-	Reduction of Area in %	40 - 50
-	-	Hardn <mark>ess in HB</mark>	111 - 121
-		Impact in Joule	-
	C % Mn % P % S % B % Fe %	C % 0.200 - 0.250 Mn % 0.300 - 0.600 P % 0.040 max. S % 0.050 max. B % 0.0008 max. Fe % Balance	C % 0.200 - 0.250 Mn % 0.300 - 0.600 P % 0.040 max. S % 0.050 max. B % 0.0008 max. Fe % Balance - - Temperion Mechanical Properion Tensile Strength in Mpa Yield Strength in Mpa Yield Strength in Mpa Elongation in % Reduction of Area in % Hardness in HB

Cross Reference Table			
Material	Standard	Country Grade Belong to the Industry	
G10230	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1023	SAE	USA	Steel
1023	AISI	USA	Steel and Bar
A 1040 1023	ASTM	USA	Steel
A 29 1023	ASTM	USA	Steel and Bar
A 29 M1023	ASTM	USA	Steel and Bar
A 513 Grade 1023	ASTM	USA	Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.