

Material - ASTM A 510 1029

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod and Round Wire

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 510 1029 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod and Round Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire Rod and Round Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 - 0.310		
Manganese	Mn %	0.600 - 0.900	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.040 max.		lizing or Hardoning and
Sulphur	S %	0.050 max.		°
Boron	В %	0.0008 max.		8
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	485 min.
-	-	-	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardne <mark>ss in BH</mark> N	-
-	-	-	Impac <mark>t in Joule</mark>	-
		-		

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
G10290	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1029	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1029	AISI	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
A 1040 1029	ASTM	USA	Steel	
A 29 1029	ASTM	USA	Steel	
A 576 10L29	ASTM	USA	Steel and Bar	
SA-29 1029	ASME	USA	Steel and Bar	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS