

## Material - ASTM A 510 1039

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod and Round Wire

**Group - Ferrous Mild Steel Alloys** 

Sub Group - ASTM A 510 1039 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod and Round Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire Rod and Round Wire

Chemical Composition			Heat Treatment	
C %	0.370 - 0.440			
Mn %	0.700 - 1.000	As Raw or Annealing or Normalizing or Hardening and Tempering		
P %	0.040 max.			
S %	0.050 max.			
В%	0.0008 max.			
Fe %	Balance			
-	-			
-	-			
-	-	Mechanical Pro	operties	
-	-	Tensile Strength in Mpa	560 - 610	
-	-	Yield Strength in Mpa	300 min.	
-	-	Elongation in %	12 min.	
-	-	Reduction of Area in %	35 - 40	
-	-	Hardness in HB	156 - 179	
-		Impact in Joule	-	
	C % Mn % P % S % B % Fe %	C % 0.370 - 0.440  Mn % 0.700 - 1.000  P % 0.040 max.  S % 0.050 max.  B % 0.0008 max.  Fe % Balance	C %         0.370 - 0.440           Mn %         0.700 - 1.000           P %         0.040 max.           S %         0.050 max.           B %         0.0008 max.           Fe %         Balance           -         -           -         Tensile Strength in Mpa           Yield Strength in Mpa           Yield Strength in Mpa           Elongation in %           Reduction of Area in %           Hardness in HB	

_						
		Cross Reference Table				
	Material	Standard	Country	Grade Belong to the Industry		
	G10390	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
	1039	SAE	USA	Steel		
	1039	AISI	USA	Steel and Bar		
	A 1040 1039	ASTM	USA	Steel		
	A 29 1039	ASTM	USA	Steel and Bar		
	A 576 10L39	ASTM	USA	Steel and Bar		
	A 830 1039	ASTM	USA	Plates and Steel		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.