

Material - ASTM A 510 1049

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rods, Round Wire and Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 510 1049 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rods, Round Wire and Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire Rods, Round Wire and Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.460 - 0.530		
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.040 max.	As Raw or Annealing or Normalizing or Hardening and Tempering	
Sulphur	S %	0.050 max.		
Boron	В%	0.0008 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	600 - 670
-	-	-	Yield Strength in Mpa	330 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	30 - 40
-	-	-	Hardness in HB	179 - 197
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	try Grade Belong to the Industry		
G10490	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1049	SAE	USA	Steel		
1049	AISI	USA	Bar		
A 830 G10490	ASTM	USA	Plate and Steel		
A 830 1049	ASTM	USA	Plate and Steel		
A 576 10L49	ASTM	USA	Steel		
A 29 1049	ASTM	USA	Steel and Bar		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.