

## Material - ASTM A 510 1053

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod, Round Rod and Steel

**Group - Ferrous Mild Steel Alloys** 

Sub Group - ASTM A 510 1053 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod, Round Rod and Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire Rod, Round Rod and Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.480 - 0.550		
Manganese	Mn %	0.700 - 1.000		
Phosphorus	P %	0.040 max.	As Raw or Annealing or Normalizing or Hardening and Tempering	
Sulphur	S %	0.050 max.		
Boron	В%	0.0008 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	770 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	220 - 260
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
G10530	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1053	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1053	AISI	USA	Steel and Bar	
A 1040 1053	ASTM	USA	Steel	
A 29 1053	ASTM	USA	Steel and Bar	
A 576 10L53	ASTM	USA	Steel and Bar	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.