

Material - ASTM A 510 1524

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Wire Rods, Round Wire and Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 510 1524 Carbon Steel Compositions For Forging To Hot-Rolled Wire Rods, Round Wire and Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire Rods, Round Wire and Steel

Chemical Composition		Heat Treatment	
C %	0.190 - 0.250		
Mn %	1.350 - 1.650	As Raw or Annealing or Normalizing or Hardening and Tempering	
P %	0.040 max.		
S %	0.050 max.		
Fe %	Balance		
-	-		
-	-		
-	-		
7	-	Mechanical Pr	operties
-	-	Tensile Strength in Mpa	510 - 570
-	-	Yield Strength in Mpa	280 min.
-	-	Elongation in %	12 min.
-	-	Reduction of Area in %	35 - 42
-	-	Hardness in HB	149 - 163
-		Impac <mark>t in Joule</mark>	-
	C % Mn % P % S % Fe %	C % 0.190 - 0.250 Mn % 1.350 - 1.650 P % 0.040 max. S % 0.050 max. Fe % Balance	C % 0.190 - 0.250 Mn % 1.350 - 1.650 P % 0.040 max. S % 0.050 max. Fe % Balance - - - - - Mechanical Propertion of Area in Material Propertion of A

Cross Reference Table				
Material	Standard	Country	Country Grade Belong to the Industry	
G15240	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1524	SAE	USA	Steel	
1524	AISI	USA	Steel and Bar	
A 29 1524	ASTM	USA	Steel and Bar	
A 830 G15240	ASTM	USA	Plate and Steel	
A 513 Grade 1524	ASTM	USA	Tubing	
A 519 1524	ASTM	USA	Tubing	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.