

## Material - ASTM A 510 1547

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod, Round Wire and Steel

**Group - Ferrous Mild Steel Alloys** 

Sub Group - ASTM A 510 1547 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod, Round Wire and Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire Rod, Round Wire and Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.430 - 0.510		
Manganese	Mn %	1.350 - 1.650	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.040 max.		alizing or Hardoning and
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		_
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	650 min.
-	-	-	Yield Strength in Mpa	360 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	40 min.
-	-	-	Hardness in HB	207 max.
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G15470	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1547	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1547	SAE	USA	Bar and Steel		
SMnC443	JIS	Japan	Steel		
NV 2	SAE	USA	Valve		
SMnC443	SAE	USA	Valve		
A 576 15L47	ASTM	USA	Steel and Bar		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.