

Material - ASTM A 510 1566

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod, Round Wire and Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 510 1566 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod, Round Wire and Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire Rod, Round Wire and Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.600 - 0.710		
Manganese	Mn %	0.850 - 1.150	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		•
Iron	Fe %	Balance		ig .
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Pro	perties
-	-	-	Tensile Strength in Mpa	1960 - 2240
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-		Impact in Joule	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
G15660	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1566	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1566	AISI	USA	Steel and Bar	
A 29 1566	ASTM	USA	Steel and Bar	
A 576 15L66	ASTM	USA	Steel and Bar	
A 713 Grade 1566	ASTM	USA	Steel and Wire	
A 713 G15660	ASTM	USA	Steel and Wire	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.