

Material - ASTM A 519 1132

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 519 1132 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.270 - 0.320		
Manganese	Mn %	1.350 - 1.650	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.080 - 0.130		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	7	-	Mechanical Pro	operties
-	-	-	Tensile Strength in Mpa	550 - 760
-	-	-	Yield Strength in Mpa	310 - 620
-	-	-	Elongation in %	12 - 23
-	-	-	Reduction of Area in %	35 - 40
-	-	-	Hardn <mark>ess in HB</mark>	164 - 217
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G11320	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1132	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1132	AISI	USA	Steel and Bar		
A 1040 1132	ASTM	USA	Steel		
A 29 1132	ASTM	USA	Steel and Bar		
A 510 1132	ASTM	USA	Wire Rod, Round Wire and Steel		
A 576 11L32	ASTM	USA	Steel and Bar		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.