



Material - ASTM A 519 1524

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 519 1524 Carbon Steel Compositions For Forging To Hot-Rolled Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.190 - 0.250	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.350 - 1.650		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	450 min
			Yield Strength in Mpa	310 min.
			Elongation in %	5 min.
			Reduction of Area in %	35 - 42
			Hardness in HRC	75 - 88
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G15240	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1524	SAE	USA	Steel
1524	AISI	USA	Steel and Bar
A 29 1524	ASTM	USA	Steel and Bar
A 510 1524	ASTM	USA	Wire Rod, Round Wire and Steel
A 830 G15240	ASTM	USA	Plate and Steel
A 513 Grade 1524	ASTM	USA	Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.