



Material - ASTM A 560 50 Cr-50 Ni

Standard Specification for Castings, Chromium-Nickel Alloy

Group - Non Ferrous Nickel Alloys

Sub Group - ASTM A 560 50 Cr-50 Ni Chromium-Nickel Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	0.300 max.	Normalising or Annealing or Hardening + Tempering	
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	48.000 - 52.000		
Iron	Fe %	1.000 Max.		
Nickel	Ni %	Balance		_
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	550 min.
-	-	-	Yield Strength in Mpa	340 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
-	-	-	-		
-	-	·	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.