

## Material - ASTM A 576 10L39

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

## **Group - Ferrous Mild Steel Alloys**

Sub Group - ASTM A 576 10L39 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.370 - 0.440		
Manganese	Mn %	0.700 - 1.000	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	Р%	0.040 max.		
Sulphur	S %	0.050 max.		
Boron	В %	0.0005 - 0.003		
Copper	Cu %	0.200 max.		
Lead	Pb %	0.150 - 0.350		
Silicon	Si %	0.100 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	560 - 610
-	-	-	Yield Strength in Mpa	300 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	35 - 40
-	-	-	Hardn <mark>ess in HB</mark>	156 - 179
-	-	-	Impac <mark>t in Joule</mark>	-
-		_		

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
G10390	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1039	SAE	USA	Steel	
1039	AISI	USA	Steel and Bar	
A 1040 1039	ASTM	USA	Steel	
A 29 1039	ASTM	USA	Steel and Bar	
A 510 1039	ASTM	USA	Wire Rod and Round Wire	
A 830 1039	ASTM	USA	Plates and Steel	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## ONE STOP SOLUTION FOR METAL PARTS