



## Material - ASTM A 576 10L46

**Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bar**

**Group - Ferrous Mild Steel Alloys**

**Sub Group - ASTM A 576 10L46 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bar**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Bar**

Chemical Composition			Heat Treatment	
Carbon	C %	0.430 - 0.500	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.700 - 1.000		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Silicon	Si %	0.100 max.		
Boron	B %	0.0005 - 0.003		
Copper	Cu %	0.200 max.		
Lead	Pb %	0.150 - 0.350		
Iron	Fe %	Balance		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	590 - 650
			Yield Strength in Mpa	320 min.
			Elongation in %	12 min.
			Reduction of Area in %	35 - 45
			Hardness in HB	170 - 187
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10460	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1046	SAE	USA	Steel
1046	AISI	USA	Steel and Bar
A 830 G10460	ASTM	USA	Plate and Steel
A 830 1046	ASTM	USA	Plate and Steel
A 510 1046	ASTM	USA	Wire Rod
A 29 1046	ASTM	USA	Steel and Bar

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.