



Material - ASTM A 576 10L53

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 576 10L53 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.480 - 0.550	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.700 - 1.000		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Boron	B %	0.0008 max.		
Copper	Cu %	0.200 max.		
Silicon	Si %	0.100 max.		
Lead	Pb %	0.150 - 0.350		
Iron	Fe %	Balance		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	770 min.
			Yield Strength in Mpa	-
			Elongation in %	12 min.
			Reduction of Area in %	-
			Hardness in HB	220 - 260
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10530	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1053	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1053	AISI	USA	Steel and Bar
A 1040 1053	ASTM	USA	Steel
A 29 1053	ASTM	USA	Steel and Bar
A 510 1053	ASTM	USA	Wire Rod, Round Rod and Steel
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.