



Material - ASTM A 576 10L55

Standard Specification for Steel Castings Bar for General Engineering Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 576 10L55 Steel Castings Bar for General Engineering Purposes
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.500 - 0.600		
Silicon	Si %	0.100 max.	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		olizing or Hardoning and
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Boron	В%	0.0005 - 0.0030		
Copper	Cu %	0.200 max.		
Lead	Pb %	0.150 - 0.350		_
Iron	Fe %	Balance	Mechanical Properties	
-	-		Tensile Strength in Mpa	650 - 660
-	-	-	Yield Strength in Mpa	360 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	30 - 40
-	-	-	Hardness in BHN	192 - 197
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
AW3	BS	British	Casting	
1055	SAE	USA	Casting	
1055	AISI	USA	Casting	
A 1040 1055	ASTM	USA	Casting	
A 29 1055	ASTM	USA	Casting	
A 510 1055	ASTM	USA	Casting	
A 682 G10550	ASTM	USA	Steel and Strip	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.