



Material - ASTM A 682 G10550

Standard Specification for Steel Castings Steel and Strip for General Engineering Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 682 G10550 Steel Castings Steel and Strip for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.500 - 0.600	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.150 - 0.300		
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.035 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 650 - 660 Yield Strength in Mpa 360 min. Elongation in % 10 min. Reduction of Area in % 30 - 40 Hardness in BHN 192 - 197 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AW3	BS	British	Casting
1055	SAE	USA	Casting
1055	AISI	USA	Casting
A 1040 1055	ASTM	USA	Casting
A 29 1055	ASTM	USA	Casting
A 510 1055	ASTM	USA	Casting
A 576 10L55	ASTM	USA	Bar

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.