



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A 684 Grade 1050

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Strip

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 684 Grade 1050 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Strip

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.480 - 0.550	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.050 max.		
Chromium	Cr %	0.250 max.		
Copper	Cu %	0.300 max.		
Silicon	Si %	0.150 - 0.300		
Nickel	Ni %	0.300 max.		
Molybdenum	Mo %	0.100 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 795 min. Yield Strength in Mpa 690 min. Elongation in % 7 min. Reduction of Area in % 20 min. Hardness in HB - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10500	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1050	SAE	USA	Steel, Sheet, Strip and Plate
1050	AISI	USA	Steel, Sheet, Strip and Plate
A 311 1050 Class A	ASTM	USA	Steel and Bar
A 311 1050 Class B	ASTM	USA	Steel and Bar
A 513 Grade 1050	ASTM	USA	Steel and Tubing
A 108 Grade 1050	ASTM	USA	Steel and Bar

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS