



## **Material - ASTM A 713 G10700**

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Steel and Wire

**Group - Ferrous Mild Steel Alloys** 

Sub Group - ASTM A 713 G10700 Carbon Steel Compositions For Forging To Hot-Rolled Steel and Wire Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.650 - 0.750		
Manganese	Mn %	0.600 - 0.900	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.040 max.		lizing or Hardoning and
Sulphur	S %	0.050 max.		-
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	/-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	640 - 700
-	-	-	Yield Strength in Mpa	390 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	30 - 45
-	-	-	Hardn <mark>ess in HB</mark>	192 - 212
-	-	-	Impa <mark>ct in Joule</mark>	-
		•		

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G10700	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1070	SAE	USA	Steel		
1070	AISI	USA	Steel and Bar		
A 510 1070	ASTM	USA	Wire Rods, Round Wire and Steel		
A 576 10L70	ASTM	USA	Steel and Bar		
A 713 Grade 1070	ASTM	USA	Steel and Wire		
A 830 1070	ASTM	USA	Plate and Steel		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.