



## Material - ASTM A 713 G10780

### Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Steel and Wire

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 713 G10780 Carbon Steel Compositions For Forging To Hot-Rolled Steel and Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.720 - 0.850	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.300 - 0.600		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	650 - 690
			Yield Strength in Mpa	380 min.
			Elongation in %	10 min.
			Reduction of Area in %	30 - 40
			Hardness in HB	192 - 207
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10780	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1078	SAE	USA	Steel
1078	AISI	USA	Steel and Bar
A 830 G10780	ASTM	USA	Plate and Steel
A 576 10L78	ASTM	USA	Steel and Bar
A 830 1078	ASTM	USA	Plate and Steel
A 713 Grade 1078	ASTM	USA	Steel and Wire

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.