



## Material - ASTM A 713 G10900

### Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Steel and Wire

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 713 G10900 Carbon Steel Compositions For Forging To Hot-Rolled Steel and Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.850 - 0.980	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	700 - 840
			Yield Strength in Mpa	460 min.
			Elongation in %	10 min.
			Reduction of Area in %	25 - 40
			Hardness in HB	197 - 248
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10900	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1090	SAE	USA	Steel and Wire
1090	AISI	USA	Steel and Wire
A 1040 1090	ASTM	USA	Steel
A 29 1090	ASTM	USA	Steel and Bar
A 510 1090	ASTM	USA	Wire Rod, Round Wire and Steel
A 576 10L90	ASTM	USA	Steel and Bar

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.