

Material - ASTM A 713 Grade 1075

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 713 Grade 1075 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.700 - 0.800		
Manganese	Mn %	0.400 - 0.700	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		•
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Pi	operties
-	-	-	Tensile Strength in Mpa	1025 min.
-	-	-	Yield Strength in Mpa	696 min.
-	-	-	Elongation in %	17.6 min.
-	-	-	Reduction of Area in %	58.2 min.
-	-	-	Hardne <mark>ss in BHN</mark>	-
-	-	-	Impact in Joule	21.7 J @ RT

Cross Reference Table					
Material	Standard	Country Grade Belong to the Industry			
G10750	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1075	SAE	USA	Steel		
1075	AISI	USA	Steel and Bar		
A 1040 1075	ASTM	USA	Steel		
A 29 1075	ASTM	USA	Steel and Bar		
A 510 1075	ASTM	USA	Steel		
A 713 G10750	ASTM	USA	Steel		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.