



Material - ASTM A 743 Grade CF-8

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 743 Grade CF-8 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	2.000 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	18.000 - 20.000		
Nickel	Ni %	8.000 - 11.000		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 485 min. Yield Strength in Mpa 205 min. Elongation in % 35 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 40.2 - 91.7 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
GX5CrNi19-10	BS	British	Plate, Tubes and Forging
1.4308	ISO	International	Casting
GX5CrNi19-10	ISO	International	Casting
A 743 J92600	ASTM	USA	Casting
A 744 Grade CF-8	ASTM	USA	Casting
G-X 6 CrNi 18 9	DIN	Germany	Casting
G-X 6 CrNi 18 9	SS	Sweden	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.