



Material - ASTM A 743 J91540

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 743 J91540 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.	Normalizing or Quenching or Solution Annealing	
Sulphur	S %	0.030 max.		
Chromium	Cr %	11.500 - 14.000		
Molybdenum	Mo %	0.400 - 1.000		
Nickel	Ni %	3.500 - 4.500		-
Iron	Fe %	Balance	Mechanical Properties	
-	-		Tensile Strength in Mpa	755 min.
-	-	-	Yield Strength in Mpa	550 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in HB	285 max.
	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
EN 10213 GX4CrNi13-4	BS	British	Plate, Tubes and Forging	
GX4CrNi13-4	ISO	International	Casting	
1.4317	ISO	International	Casting	
A 743 Grade CA-6NM	ASTM	USA	Casting	
GX4CrNi13-4	UNE	Spain	Casting	
GX4CrNi13-4	NS	Norway	Casting	
GX4CrNi13-4	AFNOR NF	France	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.