

Material - ASTM A 790 S39274

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 790 S39274 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.		
Silicon	Si %	0.800 max.		
Manganese	Mn %	1.000 max.	Solution Annealing	
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	24.000 - 26.000		
Nickel	Ni %	6.000 - 8.000		
Molybdenum	Mo %	2.500 - 3.500		•
Nitrogen	N %	0.240 - 0.320	Mechanical Properties	
Copper	Cu %	0.200 - 0.800	Tensile Strength in Mpa	800 min.
Tungsten	W %	1.500 - 2.500	Yield Strength in Mpa	550 min.
Iron	Fe %	Balance	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	310 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cycle Deference Table					
Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A240 UNS S39274	ASTM	USA	Steel, Plate, Sheet and Strip		
S39274	UNS	USA	Steel		
A789 S39274	ASTM	USA	Steel and Tube		
A815 S39274	ASTM	USA	Steel and Pipe		
A959 S39274	ASTM	USA	Steel and Pipe		
A988 S39274	ASTM	USA	Steel		
SA-789 UNS S39274	ASME	USA	Steel		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.