



**GRAVITY CAST PVT. LTD.**  
GRAVITY GROUP OF COMPANIES

## Material - ASTM A 830 1006

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets, Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 830 1006 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.450 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	300 - 330
			Yield Strength in Mpa	170 min.
			Elongation in %	20 min.
			Reduction of Area in %	45 - 55
			Hardness in HB	86 - 95
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10060	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
10060	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1006	AISI	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 1040 1006	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 29 1006	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 510 1006	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 830 G10600	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

**ONE STOP SOLUTION FOR METAL PARTS**