

Material - ASTM A 830 1038

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Plates and Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 830 1038 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Plates and Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Plates and Steel

Chemical Composition		Heat Treatment	
C %	0.350 - 0.420		
Mn %	0.600 - 0.900	As Raw or Annealing or Normalizing or Hardening and Tempering	
P %	0.030 max.		
S %	0.030 max.		•
Si %	0.150 - 0.400		ing .
Fe %	Balance		
-	-		
-	-		
-	-	Mechanical Properties	
-	-	Tensile Strength in Mpa	520 - 570
-	-	Yield Strength in Mpa	280 min.
-	-	Elongation in %	12 min.
-	-	Reduction of Area in %	35 - 40
-	-	Hardness in HB	149 - 163
-		Impac <mark>t in Joule</mark>	-
	C % Mn % P % S % Si % Fe %	C % 0.350 - 0.420 Mn % 0.600 - 0.900 P % 0.030 max. S % 0.030 max. Si % 0.150 - 0.400 Fe % Balance	C % 0.350 - 0.420 Mn % 0.600 - 0.900 P % 0.030 max. S % 0.030 max. Si % 0.150 - 0.400 Fe % Balance - - - Tensile Strength in Mpa Yield Strength in Mpa Yield Strength in Mpa Elongation in % Reduction of Area in % Hardness in HB

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
G10380	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1038	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1038	AISI	USA	Steel and Bar	
A 1040 1038	ASTM	USA	Steel	
A 29 1038	ASTM	USA	Steel and Bar	
A 510 1038	ASTM	USA	Wire Rod and Round Wire	
A 576 10L38	ASTM	USA	Steel and Bar	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.