



Material - ASTM A 830 1070

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Plate and Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 830 1070 Carbon Steel Compositions For Forging To Hot-Rolled Plate and Steel Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Plate and Steel

Chemical Comp	osition	1	Heat Treatment	
C	%	0.650 - 0.750		
se M	n %	0.600 - 0.900	As Raw or Annealing or Normalizing or Hardening and Tempering	
us P	%	0.030 max.		
S	5%	0.030 max.		•
S	i %	0.150 - 0.400		
Fe	e %	Balance		
	-	-		
	-/	-		
	_	-	Mechanical Properties	
	-		Tensile Strength in Mpa	640 - 700
	-	-	Yield Strength in Mpa	390 min.
	-	-	Elongation in %	10 min.
	-	-	Reduction of Area in %	30 - 45
	-	-	Hardness in HB	192 - 212
	-	-	Impact in Joule	-
	Se M Fus P S	C % Se	Se Mn % 0.600 - 0.900 rus P % 0.030 max. S % 0.030 max. Si % 0.150 - 0.400 Fe % Balance - -	C % 0.650 - 0.750 se

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G10700	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1070	SAE	USA	Steel		
1070	AISI	USA	Steel and Bar		
A 510 1070	ASTM	USA	Wire Rods, Round Wire and Steel		
A 576 10L70	ASTM	USA	Steel and Bar		
A 713 G10700	ASTM	USA	Steel and Wire		
A 713 Grade 1070	ASTM	USA	Steel and Wire		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.