



Material - ASTM A 830 G15240

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Plate and Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 830 G15240 Carbon Steel Compositions For Forging To Hot-Rolled Plate and Steel Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Plate and Steel

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|---------------|--|-------------------------|
| Carbon | C % | 0.190 - 0.250 | | |
| Manganese | Mn % | 1.350 - 1.650 | As Raw or Annealing or Normalizing or Hardening and Tempering | |
| Phosphorus | P % | 0.035 max. | | lizing or Hardoning and |
| Sulphur | S % | 0.040 max. | | e e |
| Iron | Fe % | Balance | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 510 - 570 |
| - | - | - | Yield Strength in Mpa | 280 min. |
| - | - | - | Elongation in % | 12 min. |
| - | - | - | Reduction of Area in % | 35 - 42 |
| - | - | - | Hardn <mark>ess in HB</mark> | 149 - 163 |
| - | - | - | Impa <mark>ct in Joule</mark> | - |

| Cross Reference Table | | | | |
|-----------------------|----------|--------------------------------------|---|--|
| Material | Standard | Country Grade Belong to the Industry | | |
| G15240 | UNS | USA | Bars, Wire Rods, Plates, Strip, Sheets and Tubing | |
| 1524 | SAE | USA | Steel | |
| 1524 | AISI | USA | Steel and Bar | |
| A 29 1524 | ASTM | USA | Steel and Bar | |
| A 510 1524 | ASTM | USA | Wire Rod, Round Wire and Steel | |
| A 513 Grade 1524 | ASTM | USA | Tubing | |
| A 519 1524 | ASTM | USA | Tubing | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS