



Material - ASTM A 866 1552

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 866 155 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.470 - 0.550	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.200 - 1.500		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.025 max.		
Silicon	Si %	0.150 - 0.350		
Aluminium	Al %	0.050 max.		
Copper	Cu %	0.300 max.		
Other	Ot %	0.002 max.		
Iron	Fe %	Balance		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	680 - 740
			Yield Strength in Mpa	410 min.
			Elongation in %	10 min.
			Reduction of Area in %	30 - 40
			Hardness in HB	193 - 217
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G15520	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1552	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1552	AISI	USA	Steel and Bar
A 29 1552	ASTM	USA	Steel and Bar
A 510 1552	ASTM	USA	Wire Rod, Round Wire and Steel
A 830 1552	ASTM	USA	Plate and Steel
A 830 G15520	ASTM	USA	Plate and Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.