

Material - ASTM A 959 S30601

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A959 S30601 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.015 max.	Solution Annealing	
Silicon	Si %	5.000 - 5.600		
Manganese	Mn %	5.000 - 5.600		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.013 max.		
Chromium	Cr %	17.000 - 18.000		
Molybdenum	Mo %	0.200 max.		
Nickel	Ni %	17.000 - 18.000		
Copper	Cu %	0.350 max.	Mechanical Properties	
Nitrogen	N %	0.050 max.	Tensile Strength in Mpa	540 min.
Iron	Fe %	Balance	Yield Strength in Mpa	255 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A240 UNS S30601	ASTM	USA	Steel, Plate, Sheet and Strip		
S30601	UNS	USA	Steel		
-	-		-		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.