

Material - ASTM A 959 S32520

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 959 S32520 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel, Sheet, Plate and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.		
Silicon	Si %	0.800 max.		
Manganese	Mn %	1.500 max.	Solution Annealing	
Phosphorus	Р%	0.035 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	24.000 - 26.000		
Nickel	Ni %	5.500 - 8.000		
Molybdenum	Mo %	3.000 - 5.000		
Nitrogen	N %	0.200 - 0.350	Mechanical Properties	
Copper	Cu %	0.500 - 3.000	Tensile Strength in Mpa	770 min.
Iron	Fe %	Balance	Yield Strength in Mpa	550 min.
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in HB</mark>	310 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
A240 UNS S32520	ASTM	USA	Steel, Plate, Sheet and Strip	
S32520	UNS	USA	Steel	
A789 S32520	ASTM	USA	Steel and Tube	
A790 S32520	ASTM	USA	Steel and Pipe	
A928 S32520	ASTM	USA	Steel and Pipe	
S32550	UNS	USA	Steel	
A240 S32550	ASTM	USA	Steel, Sheet, Plate and Strip	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS