

Material - ASTM A 959 S34565

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 959 S34565 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	5.000 - 7.000		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	23.000 - 25.000		
Molybdenum	Mo %	4.000 - 5.000		
Nickel	Ni %	16.000 - 18.000		_
Niobium	Nb %	0.100 max.	Mechanical Properties	
Nitrogen	N %	0.400 - 0.600	Tensile Strength in Mpa	795 min.
Iron	Fe %	Balance	Yield Strength in Mpa	415 min.
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A240 UNS S34565	ASTM	USA	Steel, Plate, Sheet and Strip		
S34565	UNS	USA	Steel		
A167 S34565	ASTM	USA	Steel, Sheet, Plate and Strip		
A213 S34565	ASTM	USA	Steel and Tube		
A249 S34565	ASTM	USA	Steel and Tube		
A276 S34565	ASTM	USA	Steel, Bar and Shapes		
A312 S34565	ASTM	USA	Steel and Pipe		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.