

Material - ASTM A 959 Type 334

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 959 Type 334 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.	Solution Annealing	
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	18.000 - 20.000		
Nickel	Ni %	19.000 - 21.000		
Aluminium	Al %	0.150 - 0.600		_
Titanium	Ti %	0.150 - 0.600	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	485 min.
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	92 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A240 UNS S33400	ASTM	USA	Steel, Plate, Sheet and Strip		
S22400	UNS	USA	Steel		
X8CrNiAlTi20-20	DIN	Germany	Steel		
1.4847	DIN	Germany	Steel		
1.4847	EN	European Union	Steel		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.