

## Material - ASTM A 988 S32760

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - ASTM A 988 S32760 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	24.000 - 26.000		
Nickel	Ni %	6.000 - 8.00		
Molybdenum	Mo %	3.000 - 4.000		-
Nitrogen	N %	0.200 - 0.300	Mechanical Properties	
Copper	Cu %	0.500 - 1.000	Tensile Strength in Mpa	750 - 895
Tungsten	W %	0.500 - 1.000	Yield Strength in Mpa	550 min.
Iron	Fe %	Balance	Elongation in %	25 min.
-	-	-	Reduction of Area in %	45 min.
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
A240 UNS S32760	ASTM	USA	Steel, Plate, Sheet and Strip	
S32760	UNS	USA	Steel	
A276 S32760	ASTM	USA	Steel, Bar and Shapes	
A789 S32760	ASTM	USA	Steel and Tube	
A790 S32760	ASTM	USA	Steel and Pipe	
A815 S32760	ASTM	USA	Steel and Pipe	
A959 S32760	ASTM	USA	Steel	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.