GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A131 Grade CS EH32

Standard Specification for Structural Steel for Ships

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A131 Grade CS EH32 Structural Steel for Ships

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel

Chemical Composition		
Carbon	C %	0.180 max.
Manganese	Mn %	0.900 - 1.600
Silicon	Si %	0.100 - 0.500
Phosphorus	P %	0.035 max.
Sulphur	S %	0.035 max.
Aluminium	Al %	0.015 min.
Niobium	Nb %	0.020 - 0.050
Vanadium	V %	0.050 - 0.100
Titanium	Ti %	0.020 max.
Copper	Cu %	0.350 max.
Chromium	Cr %	0.200 max.
Nickel	Ni %	0.400 max.
Molybdenum	Mo %	0.080 max.
Iron	Fe %	Balance
-	-	-

Heat Treatment
As-Raw or Annealing or Normalizing or Normalizing & Tempering or Quenching & Tempering

Mechanical Properties	
Tensile Strength in Mpa	440 - 590
Yield Strength in Mpa	315 min.
Elongation in %	22 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	50 @ -40˚C

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
5521 A32	GOST	Russia	Plates
8324 D 32	STAS	Romania	Plates
9801 10 G2-K	BDS	Bulgaria	Steel
1.0515	DIN	Germany	Steel
GL-E 32 (S 315 G 3 S)	DIN	Germany	Steel
92147 AH 32	PN	Poland	Plates
92147 DH 32	PN	Poland	Plates

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.