GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A131 Grade D

Standard Specification for Structural Steel for Ships

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A131 Grade D Structural Steel for Ships

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel

Chemical Composition		
Carbon	C %	0.210 max.
Manganese	Mn %	0.600 min.
Silicon	Si %	0.100 - 0.350
Phosphorus	P %	0.035 max.
Sulphur	S %	0.035 max.
Nickel	Ni %	0.020 max.
Chromium	Cr %	0.020 max.
Molybdenum	Mo %	0.020 max.
Copper	Cu %	0.020 max.
Cr + Mn/6	Cr % + Mn/6 %	0.400 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Annealing or Normalizing or Normalizing & Tempering or Quenching & Tempering

Mechanical Properties	
Tensile Strength in Mpa	400 - 520
Yield Strength in Mpa	235 min.
Elongation in %	24 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	41 @ -20˚C

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
K01400	UNS	USA	Steel
1.0032	EN	European Union	Steel
S 250 GT	EN	European Union	Steel
2393-2 1.0032	DIN	Germany	Steel and Tubing
2394-2 1.0032	DIN	Germany	Steel and Tubing
17140-1 1.0010	DIN	Germany	Wire Rods
17140-1 D 9	DIN	Germany	Wire Rods

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.