



Material - ASTM A176 S44400

Standard Specification for Stainless and Heat-Resisting Chromium Steel Plate, Sheet, and Strip

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A176 S44400 Stainless and Heat-Resisting Chromium Steel Plate, Sheet, and Strip

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.025 max.	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	17.500 - 19.500		
Molybdenum	Mo %	1.750 - 2.500		
Nickel	Ni %	1.000 max.	Mechanical Properties	
Ti + Nb	Ti% + Nb%	0.800 max.	Tensile Strength in Mpa	415 min.
Nitrogen	N %	0.035 max.	Yield Strength in Mpa	275 min.
Iron	Fe %	Balance	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	217 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
444	AS	Australia	Plate, Sheet and Strip
SA-731 18 Cr-2Mo	ASTM	USA	Casting
F.3123	UNE	Spain	Casting
S44400	UNS	USA	Plate, Sheet and Strip
X 2 CrMoTiNb 18-2	UNE	Spain	Plate, Sheet and Strip
444	SAE	USA	Plate, Sheet and Strip
A731 18Cr-2Mo	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.