GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A182 F6a Class4

Standard Specification for Forged or Rolled Alloy-Steel Pipe Flanges, Forged Fittings, and Valves and Parts for High-Temperature Service

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A182 F6a Class4 Forged or Rolled Alloy-Steel Pipe Flanges, Forged Fittings, and Valves and Parts for High-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Pipe, Bars and Forging

Chemical Composition		
Carbon	C %	0.150 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Nickel	Ni %	0.500 max.
Chromium	Cr %	11.500 - 13.500
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing or Normalizing & Tempering

Mechanical Properties	
Tensile Strength in Mpa	895 min.
Yield Strength in Mpa	760 min.
Elongation in %	12 min.
Reduction of Area in %	35 min.
Hardness in HB	263 - 321
Impact in Joule	-

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S41000	UNS	USA	Bars, Wire, Shapes and Forging
SAE AMS-QQ-S-763 410	AISI	USA	Steel
A 193 B6	ASTM	USA	Steel
A 193 B6X	ASTM	USA	Steel
A 194 Grade 6	ASTM	USA	Steel
A 511 MT410	ASTM	USA	Steel
A 493 Type 410	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.