GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A182 FXM-19

Standard Specification for Forged or Rolled Alloy-Steel Pipe Flanges, Forged Fittings, and Valves and Parts for High-Temperature Service

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A182 FXM-19 Forged or Rolled Alloy-Steel Pipe Flanges, Forged Fittings, and Valves and Parts for High-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Pipe, Bars and Forging

Chemical Composition		
Carbon	C %	0.060 max.
Manganese	Mn %	4.000 - 6.000
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Nickel	Ni %	11.500 - 13.500
Chromium	Cr %	20.500 - 23.500
Niobium	Nb %	0.100 - 0.300
Molybdenum	Mo %	1.500 - 3.000
Nitrogen	N %	0.200 - 0.400
Vanadium	V %	0.100 - 0.300
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	690 min.
Yield Strength in Mpa	380 min.
Elongation in %	35 min.
Reduction of Area in %	55 min.
Hardness in HB	-
Impact in Joule	-

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
J 405 XM-19	SAE	USA	Steel
S20910	UNS	USA	Steel
A 358 XM-19	ASTM	USA	Steel and Pipe
A 336 Grade FXM-19	ASTM	USA	Steel and Forging
A 314 XM-19	ASTM	USA	Bars and Forging
A 479 XM-19	ASTM	USA	Steel and Bars
A 580 Type XM-19	ASTM	USA	Steel and Wire

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.