GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A204 Grade C

Standard Specification for Pressure Vessel Plates, Alloy Steel, Molybdenum

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A204 Grade C Pressure Vessel Plates, Alloy Steel, Molybdenum

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plates

Chemical Composition		
Carbon	C %	0.230 max.
Manganese	Mn %	0.900 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.035 max.
Silicon	Si %	0.150 - 0.400
Molybdenum	Mo %	0.450 - 0.600
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Normalizing or Stress Relieved

Mechanical Properties	
Tensile Strength in Mpa	515 - 655
Yield Strength in Mpa	295 min.
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
A 672 Grade L 75	ASTM	USA	Steel and Pipe
A 691 Grade CM-75	ASTM	USA	Steel and Pipe
A 691 Grade C70	ASTM	USA	Steel and Pipe
G 3103 SB 480 M	JIS	Japan	Plates
G 3103 SB 49 M	JIS	Japan	Plates
SA-691 CM-70	ASME	USA	Steel and Pipe
SA-691 CM-75	ASME	USA	Steel and Pipe

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.