GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A213 T11

Standard Specification for Seamless Ferritic and Austenitic Alloy-Steel Boiler, Superheater, and Heat-Exchanger Tubes

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A213 T11 Seamless Ferritic and Austenitic Alloy-Steel Boiler, Superheater, and Heat-Exchanger Tubes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel Tubes

Chemical Composition		
Carbon	C %	0.050 - 0.150
Manganese	Mn %	0.300 - 0.600
Phosphorus	P %	0.025 max.
Sulphur	S %	0.025 max.
Silicon	Si %	0.500 - 1.000
Chromium	Cr %	1.000 - 1.500
Molybdenum	Mo %	0.440 - 0.650
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing or Normalizing or Tempering

Mechanical Properties	
Tensile Strength in Mpa	-
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HBW	-
Impact in Joule	-

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
K11597	UNS	USA	Steel and Pipe
SA-199 Grade T11	ASME	USA	Steel and Tubing
SA-250 Grade T11	ASME	USA	Steel and Tubing
A 369 Grade FP11	ASTM	USA	Steel and Pipe
A 250 Grade T11	ASTM	USA	Steel and Tubing
A 335 Grade P11	ASTM	USA	Steel and Pipe
A 200 Grade T11	ASTM	USA	Steel and Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.