

Material - ASTM A216 WCA

Standard Specification for Steel Castings, Carbon, Suitable for Fusion Welding, for High-Temperature Service

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A216 / A216M Steel Castings, Carbon, Suitable for Fusion Welding, for High-Temperature Service Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|------------|---|-----------|
| Carbon | C % | 0.250 max. | | |
| Silicon | Si % | 0.600 max. | | |
| Manganese | Mn % | 0.700 max. | | |
| Phosphorus | P % | 0.035 max. | Normalising or Annealing or Hardening + Tempering | |
| Sulphur | S % | 0.035 max. | | |
| Chromium | Cr % | 0.500 max. | | |
| Nickel | Ni % | 0.500 max. | | |
| Molybdenum | Mo % | 0.200 max. | | _ |
| Copper | Cu % | 0.300 max. | Mechanical Properties | |
| Vanadium | V % | 0.030 max. | Tensile Strength in Mpa | 415 - 585 |
| other | Ot % | 1.000 max. | Yield Strength in Mpa | 205 min. |
| Iron | Fe % | Balance | Elongation in % | 24 min. |
| - | - | _ | Reduction of Area in % | 35 min. |
| - | - | - | Hardness in BHN | - |
| - | - | | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | |
|-----------------------|----------|----------------|-------------------------------------|--|
| Material | Standard | Country | ry Grade Belong to the Industry | |
| SA 216 WCA | ASME | USA | Casting | |
| A660 WCA | ASTM | USA | Fusion Welding, Bending and Forming | |
| J02502 | UNS | USA | Casting | |
| A216 WCB | ASTM | USA | Casting | |
| SA 216 WCB | ASME | USA | Casting | |
| 1.0619 | EN | European Union | Casting | |
| 1.0619 | WN | Germany | Casting | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.