

Material - ASTM A216 WCB

Standard Specification for Steel Castings, Carbon, Suitable for Fusion Welding, for High-

Temperature Service

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A216 / A216M Steel Castings, Carbon, Suitable for Fusion Welding, for High-Temperature Service Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition		Heat Treatment	
C %	0.300 max.		
Si %	0.600 max.		
Mn %	1.000 max.		
Р%	0.035 max.	Normalising or Annealing or Hardening + Tempering	lardening + Tempering
S %	0.035 max.		
Cr %	0.500 max.		
Ni %	0.500 max.		
Mo %	0.200 max.		
Cu %	0.300 max.	Mechanical Properties	
V %	0.030 max.	Tensile Strength in Mpa	485 - 655
Ot %	1.000 max.	Yield Strength in Mpa	250 min.
Fe %	Balance	Elongation in %	22 min.
-	-	Reduction of Area in %	35 min.
-	-	Hardne <mark>ss in BHN</mark>	-
-		Impac <mark>t in Joule</mark>	-
	C % Si % Mn % P % S % Cr % Ni % Mo % Cu % V % Ot % Fe % -	C % 0.300 max. Si % 0.600 max. Mn % 1.000 max. P % 0.035 max. S % 0.035 max. Cr % 0.500 max. Ni % 0.500 max. Mo % 0.200 max. V % 0.030 max. V % 0.030 max. Fe % Balance	C % 0.300 max. Si % 0.600 max. Mn % 1.000 max. P % 0.035 max. S % 0.035 max. Cr % 0.500 max. Ni % 0.500 max. Mo % 0.200 max. V % 0.030 max. V % 0.030 max. V % 0.030 max. Tensile Strength in Mpa Ot % 1.000 max. Fe % Balance Elongation in % - - Hardness in BHN

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
SA 216 WCB	ASME	USA	Casting	
A757 A1Q	ASTM	USA	Casting	
J03002	UNS	USA	Casting	
1.0619	WN	Germany	Casting	
1.0619	EN	European Union	Casting	
A660 WCB	ASTM	USA	Fusion Welding, Bending and Forming	
SA 660 WCB	ASME	USA	Centrifugal Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS