

Material - ASTM A217 Grade WC9

Standard Specification for Steel Castings, Martensitic Stainless and Alloy, for Pressure-Containing Parts, Suitable for High-Temperature Service

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A217 / A217M Steel Castings, Martensitic Stainless and Alloy, for Pressure-Containing Parts, Suitable for High-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.180		
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.400 - 0.700		
Phosphorus	P %	0.035 max.	Normalising or Annealing or	Hardening + Tempering
Sulphur	S %	0.035 max.		
Chromium	Cr %	2.000 - 2.750		
Nickel	Ni %	0.500 max.		
Molybdenum	Mo %	0.900 - 1.200		
Copper	Cu %	0.500 max.	Mechanical Pr	operties
Tungsten	W %	0.100 max.	Tensile Strength in Mpa	485 - 655
other	Ot %	1.000 max.	Yield Strength in Mpa	275 min.
Iron	Fe %	Balance	Elongation in %	20 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
J21890	UNS	USA	Casting	
SA-217 Grade WC9	ASME	USA	Casting	
10 CrMo 9-10	AFNOR NF	France	Steel	
622	BS	British	Bar	
10 CrMo 9-10	DIN	Germany	Forging	
10 CrMo 9-10	EN	European Union	Casting	
10 CrMo 9-10	UNI	Italy	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.